

Grey Resin V5

An optimally-balanced Grey Resin for versatile applications

Grey Resin V5 is an exceptionally versatile General Purpose Resin, offering an optimal balance of fast print speed, high accuracy, presentation-ready appearance, strong mechanical properties, and an easy, reliable workflow.

Create parts that are stiff and strong with a surface finish that rivals injection molding. Grey Resin V5 has a rich, matte color that captures fine features accurately.

Grey Resin V5 is a new material formulation that leverages the Form 4 ecosystem to print three times faster than the previous version.

Form and fit prototyping

Presentation-ready models with fine features and intricate details

General dental models

Jigs and fixtures



V5

FLGPGR05

* May not be available in all regions

Prepared: March 20, 2024

Rev. 01 March 20, 2024

To the best of our knowledge the information contained herein is accurate. However, Formlabs, Inc. makes no warranty, expressed or implied, regarding the accuracy of these results to be obtained from the use thereof.

MATERIAL PROPERTIES DATA

Grey Resin V5

| | METRIC ¹ | | | IMPERIAL ¹ | | | METHOD |
|----------------------------------|---------------------|---|---|-----------------------|---|--|---------------|
| | Green | Post-Cured 5 min (Ambient) ² | Post-Cured 15 min at 60 °C ³ | Green | Post-Cured 5 min (Ambient) ² | Post-Cured 15 min at 140 °F ³ | |
| Tensile Properties | | | | | | | |
| Ultimate Tensile Strength | 46 MPa | 54 MPa | 62 MPa | 6672 psi | 7832 psi | 8992 psi | ASTM D638-14 |
| Tensile Modulus | 2200 MPa | 2500 MPa | 2675 MPa | 319 ksi | 363 ksi | 388 ksi | ASTM D638-14 |
| Elongation at Break | 22% | 15% | 13% | 22% | 15% | 13% | ASTM D638-14 |
| Flexural Properties | | | | | | | |
| Flexural Strength | 82 MPa | 91 MPa | 103 MPa | 11893 psi | 13198 psi | 14938 psi | ASTM D790-15 |
| Flexural Modulus | 2000 MPa | 2450 MPa | 2750 MPa | 290 ksi | 355 ksi | 399 ksi | ASTM D790-15 |
| Impact Properties | | | | | | | |
| Notched Izod | 36 J/m | 34 J/m | 32 J/m | 0.673 ft-lbs/in | 0.636 ft-lbs/in | 0.598 ft-lbs/in | ASTM D4812-11 |
| Thermal Properties | | | | | | | |
| Heat Deflection Temp. @ 1.8 MPa | 54 °C | 54 °C | 59 °C | 129 °F | 129 °F | 138 °F | ASTM D648-16 |
| Heat Deflection Temp. @ 0.45 MPa | 62 °C | 62 °C | 71 °C | 144 °F | 144 °F | 160 °F | ASTM D648-16 |

SOLVENT COMPATIBILITY

Percent weight gain over 24 hours for a printed and post-cured 1 x 1 x 1 cm cube immersed in respective solvent:

| Solvent | 24 hr weight gain, % | Solvent | 24 hr weight gain, % |
|---------------------------------|----------------------|--|----------------------|
| Acetic Acid 5% | 0.9 | Mineral oil (Heavy) | 0.2 |
| Acetone | 4.9 | Mineral oil (Light) | 0.2 |
| Bleach ~5% NaOCl | 0.7 | Salt Water (3.5% NaCl) | 0.8 |
| Butyl Acetate | 0.3 | Skydrol 5 | 0.5 |
| Diesel Fuel | 0.1 | Sodium Hydroxide solution (0.025% PH 10) | 0.8 |
| Diethyl glycol Monomethyl Ether | 1.0 | Strong Acid (HCl conc) | 0.5 |
| Hydraulic Oil | 0.2 | Tripropylene glycol monomethyl ether | 0.3 |
| Hydrogen peroxide (3%) | 0.9 | Water | 0.8 |
| Isooctane (aka gasoline) | < 0.1 | Xylene | < 0.1 |
| Isopropyl Alcohol | 0.3 | | |

¹ Material properties may vary based on part geometry, print orientation, print settings, temperature, and disinfection or sterilization methods used.

² Data was obtained from parts printed on a Form 4 printer with 100 µm Grey Resin V5 settings, washed in a Form Wash for 5 minutes in ≥99% Isopropyl Alcohol, and post-cured at room temperature for 5 minutes in a Form Cure.

³ Data was obtained from parts printed on a Form 4 printer with 100 µm Grey Resin V5 settings, washed in a Form Wash for 5 minutes in ≥99% Isopropyl Alcohol, and post-cured at 60°C for 15 minutes in a Form Cure.